



Product name	:	MoTip Industrial Zinc Repair Spray
Article number	:	07304
Supplier / Producer	:	MOTIP DUPLI B.V.
		Wolframweg 2
		NL-8471 XC WOLVEGA
		Telephone number +31 561 – 69 44 00
		Telefax number +31 561 – 69 44 31

Product description

High quality zinc repair spray to repair minor damage in surfaces of steel galvanised by immersion.

Product characteristics

Fast drying
Good coverage
Non-fading and UV resistant
Good surface hardness
Resistant to petrol, chemicals and weather influences
Wear resistant and scratch free
Excellent adhesion

Physical and Chemical Characteristics

Contents	:	500 ml
Base	:	Nitro-cellulose binder
Colour	:	Silver
VOC-content	:	Approximately 93% w/w
Solid content	:	Approximately 7% w/w
Coverage	:	1,5 to 2 m ²
Dust dry	:	After 5 to 10 minutes
Tack free	:	After 10 to 20 minutes
Hardened/re-sprayable	:	After 2 hours
Heat resistant	:	To 110°C

Usage

Before use, carefully read the directions on the packaging and act accordingly.

Pre Treatment

The surface should be clean, dry and free of grease.

Treatment

The aerosol should have room temperature. Best processing temperature 15 to 25°C. Before use, shake the aerosol for 2 minutes and spray a sample. Distance to the surface to be treated approximately 25 to 30 centimetre.

Apply the zinc repair spray in several thin layers. Before applying the next layer, again shake the aerosol..

After use, clean the valve (turn aerosol upside down and press the nozzle for approximately 5 seconds).

The drying time depends on the ambient temperature, the humidity of the air and the thickness of the lacquer applied.